


PRODUCT CODE:
A-122

DATASHEET NO:
KPME-B-02

ISSUE DATE:
OCTOBER 2014



PRODUCT DESCRIPTION

KANSAI EXTERIOR STUCCO is a ready to use water based filler that has excellent whiteness, coverage and application properties. Its high quality filling properties make it ideal for use on all types of exterior masonry surfaces. It provides a smooth base for the application of exterior architectural coating products.

INTENDED USAGE

- To prepare wood and masonry surfaces for paint application.

FEATURES & BENEFITS

- Excellent coverage, whiteness and hiding power.
- Creates a smooth, uniform surface on which paint can be readily applied.

PHYSICAL PROPERTIES

Appearance

Matt

Colours

White

Generic Type

Acrylic Copolymer

Volume Solids

Approx. 60%

Specific Gravity at 23°C

1,8 (approx.)

Recommended DFT per coat

Min: 80 µm Max: 120 µm

Flash Point

N.A.

Theoretical Spreading Rate

6 m²/litre @ 100 µm DFT

APPLICATION DETAILS

Mixing

Ready to use.

Substrate

Thoroughly prepared concrete, plaster, brickwork and various building boards.

Method

Putty knife.

Thinning

Ready for use by trowel application.

Cleaning

Water.

Application Environment

	Surface Temperature	Ambient Temperature	Relative Humidity
Min	10 °C	10 °C	10%
	Or 2 °C min. above dew point		
Max	40 °C	50 °C	85%

Drying Time

Touch Dry	2h at 23 °C
Recoating	6h at 23 °C
Dry to handle	6h at 23 °C

SURFACE PREPARATION GUIDELINES

Ensure that surfaces are dry, sound and free from dust, dirt, grease and oil before painting.

A. NEW WORK:

- Cement plaster, concrete, gypsum plaster:
 - 1.1. New or bare surfaces must be clean, dry and free from masonry salts.
 - 1.2. Remove all defective or poorly adhering material by rubbing down using a suitable abrasive paper or stiff brush and dust off.
 - 1.3. Treat any area affected by mould, lichens, algae or moss with bleach.
 - 1.4. After priming new surfaces with **KANSAI ALLPURPOSE PRIMER**.
 - 1.5. Proceed to filling.
- Fiber Cement:
 - 2.1. Prime with **KANSAI ALLPURPOSE PRIMER**.
 - 2.2. Proceed to filling.
- Wood:
 - 3.1. Prime with **KANSAI ALKYD PRIMER**.
 - 3.2. Proceed to filling by applying one coat of **KANSAI EXTERIOR STUCCO** to level surface.

PRODUCT CODE:
A-122

DATASHEET NO:
KPME-B-02

ISSUE DATE:
OCTOBER 2014

B. PREVIOUSLY PAINTED SURFACES IN GOOD CONDITION:

1. Remove loose and flaking paint back to a sound substrate and a firm edge by scraping and sanding. Spot prime bare areas with **KANSAI ALLPURPOSE PRIMER**.

C. PREVIOUSLY PAINTED SURFACES IN POOR CONDITION:

1. Completely remove paint by most appropriate means e.g. scraping, coarse sanding
2. Prime the surface using **KANSAI ALLPURPOSE PRIMER**.
3. Proceed to filling.

D. Filling

1. Fill defects with **KANSAI EXTERIOR STUCCO** for exterior surfaces. Allow it to dry before applying second coat. Third coat is recommended for extra smoothness. After drying, scuff surface using abrasive paper and dust off.

APPLICATION PROCEDURE

- Apply by putty knife or trowel after the application of suitable primer.

STORAGE & PACKAGING

- Store away from direct sun, heat and severe cold.
- Packaging: 4.0 L & 18.0 L

CAUTIONS

- Friable and powdery surfaces require special care before painting - if in doubt contact manufacturer.
- For health reasons avoid dusting when preparing fiber cement surfaces. Keep surfaces wet and wash off residues with water.
- Do not paint under conditions of frost, dew, rain, fog or inclement weather. Note: Painting under the above conditions may affect the performance of the paint film.
- Avoid painting during inclement weather or if temperature is below 10 °C.

SAFETY PRECAUTIONS

- Keep out of reach of children.
- Ensure good ventilation during application and drying.
- In case of skin contact, wash with soap and water or a recognized skin cleaner.
- Avoid contact with eyes – In case of contact, rinse eyes immediately with plenty of water and seek medical advice if symptoms persist.
- Harmful if swallowed. Do not induce vomiting. Seek medical attention.
- Refer to Material Safety Data Sheet for complete information.